

STAUF SMP-920 woodflooring adhesive

1-component elastic SMP wood flooring adhesive according to DIN EN 14293 for parquet

Special features:

- ▶ elastic
- ▶ tension-reducing parquet bonding
- ▶ excess adhesive easy to remove
- ▶ water and solvent-free
- ▶ no wood swelling



Suitable for installation of

- ▶ multiple layer wood flooring according to DIN EN 13489
- ▶ wood strip flooring raw according to DIN EN 13226, max. 75 x 600 mm, min. 14 mm thickness

Suitable sub floors

- ▶ cement floors
- ▶ calcium sulphate (flow) floors
- ▶ chipboards V100 (E1), OSB boards
- ▶ STAUF levelling compounds for wood flooring
- ▶ mastic asphalt screed, only after priming with STAUF VEP-190

Suitable primers

- ▶ STAUF VDP-130
- ▶ STAUF VPU-155
- ▶ STAUF VEP-190
- ▶ STAUF VSP-110

Suitable levelling compounds

- ▶ STAUF SPP-95
- ▶ STAUF SPP-90
- ▶ IBOLA FZ
- ▶ IBOLA RM
- ▶ IBOLA PU

Suitable underlays

- ▶ STAUF polyester fleece
- ▶ STAUF Decoupling/stress relief board

Product properties

- ▶ aging-resistant
- ▶ very well spreadable
- ▶ elastically deformable
- ▶ not sensitive to frost
- ▶ fast setting

Color

- ▶ beige

Required quantities per m²

- ▶ 1050 g with STAUF notched trowel no. 3 (TKB B7)
- ▶ 1300 g with STAUF notched trowel no. 4 (TKB B15)
- ▶ 1150 g with STAUF notched trowel no. 5 (TKB B9)

Open time

- ▶ approx. 30 minutes at 20 °C

Accessibility

- ▶ after approx. 48 hours

Room climate at work site

- ▶ minimum 15 °C, maximum 75% rel. humidity, preferably max. 65%

Shelf-life

- ▶ minimum 9 months

Available Packaging

- ▶ 18 kg plastic bucket

Ecode

- ▶ EC1-R

Giscode

- ▶ RS 10

Examination of sub floor

Prior to processing, the sub floor must be checked according to the standard DIN 18356 or corresponding national standards. The sub floor shall be resistant to pressure and tension, free of cracks, must have sufficient surface strength, be permanently dry, level, clean and free of anti-adherents, sinter layers etc. In addition, porosity and grip of surface need to be checked. Also check moisture content and absorptive capacity of cement (flow) and calciumsulfate (flow) floors as well as room temperature, air humidity and sub floor temperature.

Sub floor preparation

It must be ensured that the sub floor is ready for installation by performing proper sub floor preparation, floors must be clean, have sufficient surface strength, must be level, permanently dry and free of cracks. A mechanical pretreatment of the subfloor (sweeping, vacuuming, mechanical brushing, sanding, milling, shot blasting) must be performed depending on type and condition of sub floor. Cracks and joints, except expansion joints and other construction joints, shall be solidly closed with STAUF casting resin and floor brackets. Cavities and indentations can be filled with a non self-levelling STAUF levelling compound. If necessary, make sure sub floors are level, have sufficient absorptive capacity and grip by applying the appropriate STAUF levelling compound.

Processing

Apply adhesive to sub floor using the appropriate STAUF notched trowel, avoid adhesive pooling and excessive layer thickness by evenly raking the notched trowel over adhesive layer. Install wood flooring during specified open time, slide in and press down firmly. In particular with raw wood flooring, avoided pushing adhesive into joints. Adhesive in joints can impair subsequent surface treatment. Depending on the degree of setting, adhesive residues can be removed with the appropriate STAUF cleaners. Please test the effect of the cleaner on the finish of the wood flooring in an inconspicuous area or on a sample prior to applying the cleaner. Hardened adhesive residues can easily be removed mechanically, mostly residue-free. However, longer exposures on finished wood flooring should be avoided to prevent possible contouring.

Accessibility

Load bearing capacity depends on room climate and applied quantities of adhesive.

Other information

Plasticizers contained in the adhesive can cause flow asphalts to partially dissolve and may affect the wood flooring finish, especially for wood flooring installed without tongue and groove technique. For installation of wood flooring types without tongue and groove technique and for large-format solid planks, we recommend using only elastic adhesives with some reservations on account of limited dimensional stability. For these types of wood flooring, we recommend using of hard-elastic STAUF polyurethane adhesives (PUK series) or hard-elastic dispersion adhesives (STAUF M2A series). In case an elastic bonding is desired, please use STAUF adhesives without softening ingredients. The adhesive hardens when reacting with moisture either in the form of air humidity, wood or substrate moisture. The higher the ambient temperature, the faster the adhesive sets. Setting time increases with thickness of the adhesive layer. Adhesives classified as „elastic“ according to DIN EN 14293, have elastic properties once hardened. On account of this elasticity, only minimal tension is transferred from parquet to sub floor, but dimensional changes of the parquet elements are allowed for.

Limitation of liability

The foregoing representations are based on the results of our most current product and material testing and are of a non-obligatory advisory nature only since we have no control over the actual quality of workmanship, materials used and worksite conditions. As such, they do not constitute an express or implied warranty of any kind. The same applies to our commercial and technical consultation services which are provided free-of-charge and without obligation. Therefore, we strongly recommend that prior on-site testing be conducted to observe and study the suitability of the product for the intended purpose. With the release of this technical information, all prior technical information (technical data sheets, installation recommendations and other information regarding similar purposes) becomes invalid.